

MARUYASU Corporation

3-21-5 RYOGOKU SUMIDAKU TOKYO 130 0026 JAPAN www.maruyasu-fil.co.jp

TECHNICAL DETAILS

YARN DESCRIPTION: BALLOON COTTON 5

COMPOSITION: COTTON 50%, BULKY ACRYLIC 50%

COUNT: Nm 1/4

TYPE OF DYEING: Hank/ About 250g per hank

KNITTING: 5G-1P

STOCK SERVICE: YES

Minimum=1.0kg

L/T:dyeing=3-4weeks

OWN COLOR: YES

Minimum=3.0kg

L/T:dyeing=3-4weeks

**NOTE: In case no stock of RW / spinning=8-10weeks+dyeing 3-4weeks

FINISHING: • Washing for 10 min with some softener (Water temp. 35°C)

- · Dewatering for 1min
- · Tumble dry for 3min
- $\boldsymbol{\cdot}$ Press with a lot of steam

※ It is necessary to make specific trials in your own knits before starting production since the final result always depends on your equipment and the tension and stitch you choose.

SPECIAL CARES: 1. The cone should not be rewinded since not appropriate winding could

jeapardize the yarn quality.

2. This yarn is dyed in hunks, and has the knots in composition, please knit

with care to avoid the knots

CARE INSTRUCTION:













