

TECHNICAL DETAILS

| | |
|--------------------|---|
| YARN DESCRIPTION : | BENSOLO |
| COMPOSITION: | CUPRO 60% POLYESTER40% |
| COUNT: | Nm.1/72 |
| TYPE OF DYEING: | Cone |
| KNITTING: | 16G-2PLY |
| STOCK SERVICE: | YES Minimum=1.0kg L/T:dyeing=2-3weeks |
| OWN COLOR: | YES Minimum=5.0kg L/T:dyeing=2-3weeks ※NOTE: In case no stock of RW / spinning=6-8weeks+dyeing 2-3weeks |
| FINISHING: | <ul style="list-style-type: none"> • Washing 10 min with some softener (Water temp. 35°C) • Dehydrator 1min • Drying 3min • Press with a lot of steam. ※It is necessary to make specific trials in your own knits before starting production since the final result always depends on your equipment and the tension and stitch you choose. |
| SPECIAL CARES: | <ol style="list-style-type: none"> 1. The cone should not be rewinded since not appropriate winding could jeopardize the yarn quality. 2. This yarn is dyed in cones and it may have the color differences between inside and outside of cones. We recommend to knit with more thread guides. We pay attention to this color difference, and We are not able to guarantee this problem if you have. 3. Please iron with a cloth to avoid shiny marks on the surface. |

CARE INSTRUCTION:

