

## MARUYASU Corporation

3-21-5 RYOGOKU SUMIDAKU TOKYO 130 0026 JAPAN www.maruyasu-fil.co.jp

## **TECHNICAL DETAILS**

YARN DESCRIPTION :	ERICA
COMPOSITION:	COTTON86% POLYESTER14%
COUNT:	Nm.1/7.4
TYPE OF DYEING:	Hank/ About 330g per hank
KNITTING:	7G-1PLY
STOCK SERVICE:	YES Minimum=1.0kg L/T:dyeing=3-4weeks
OWN COLOR:	YES <u>Minimum=3.0kg</u> <u>L/T:dyeing=3-4weeks</u> WOTE: In case no stock of RW / spinning=6-8weeks+dyeing 3-4weeks
FINISHING:	<ul> <li>Washing for 10 min with some softener (Water temp. 35°C)</li> <li>Dewatering for 1min</li> <li>Tumble dry for 3min</li> <li>Press with a lot of steam</li> <li>X It is necessary to make specific trials in your own knits before starting production since the final result always depends on your equipment and the tension and stitch you choose.</li> </ul>
SPECIAL CARES:	<ol> <li>The cone should not be rewinded since not appropriate winding could jeapardize the yarn quality.</li> <li>This yarn is dyed in hunks, and has the knots in composition, please knit with care to avoid the knots</li> </ol>
CARE INSTRUCTION:	