

QUALITY TESTING REPORT



F a b r i c T e s t	Item	Methods	1	①SR07 WHITE	2	②SR07 WHITE	3	4	5	6	
		Water repellency (G)	JIS L 1092 Spray Method		3*/3*/3*		3*/3*/3*				
	Water repellency (G)	JIS L 1092 Spray Method After Wahing cleaning	3times	3*/3*/3*		3*/3*/3*					
			5times	3*/3*/3*		3*/3*/3*					
			10times	3*/3*/3*		3*/3*/3*					
			15times	3*/3*/3*		3*/3*/3*					
			20times	3*/3*/3*		3*/3*/3*					
	Water repellency (G)	JIS L 1092 Spray Method After Drying cleaning		3*/3*/3*		3*/3*/3*					

Buyer	Company Name	
	District/Store Name	
	Assort Code	
	Item Code	


Seller	Company Name	MARUYASU Corporation
	Address	3-21-5 Ryougoku Sumida-ku Tokyo Japan
		03-3633-5561
	Person in charge	Wang

Description	Proof PLUS α	
	①16G-3P plain stitch ②16G-2P rib stitch No. of colour 2	
	Adjacent fabric	

Assessment	Standard	/	
	Fabric Test	PASS	Col. - FAIL Col.

Remark:
 Washing: JIS L 1092 6.2.1 c) Line dry
 Drying : JIS L 1092 6.2.2 b) 4)
 *Leakage phenomenon occurring between the spaces from back side.

C : Color Fastness (G) : Grade



BOKEN BOKEN QUALITY EVALUATION INSTITUTE Softline Division Tokyo Testing Center		Checked by	Taka hashi
		Approved by	
Reception Date	2022 Y 8 M 30 D	No.	
Tissue Date	2022 Y 9 M 12 D	30122024750	-1 (End)