

## **MARUYASU Corporation**

3-21-5 RYOGOKU SUMIDAKU TOKYO 130 0026 JAPAN www.maruvasu-fil.co.ip

## **TECHNICAL DETAILS**

YARN DESCRIPTION: LEGER DEKNIT

COMPOSITION: WOOL14% RAYON56% NYLON30%

COUNT: Nm 1/60

TYPE OF DYEING: KNITTED GARMENT

KNITTING: 16G-1PLY

STOCK SERVICE: YES

Minimum=1kg

L/T:dyeing 4-5weeks

OWN COLOR: YFS

Minimum=3kg

L/T:dyeing=4-5weeks

\*\*NOTE: In case no stock of RW / spinning 4-5weeks+dyeing 4-5weeks

FINISHING: · Washing 5 min with some softener (Water temp. 35°C)

· Dehydrator 1min

· Drying 3min

· Press with a lot of steam.

XIt is necessary to make specific trials in your own knits before starting production since the final result always depends on your equipment and

the tension and stitch you choose.

SPECIAL CARES: 1. The cone should not be rewinded since not appropriate winding could

jeapardize the yarn quality.

CARE INSTRUCTION:









