

MARUYASU Corporation

3-21-5 RYOGOKU SUMIDAKU TOKYO 130 0026 JAPAN www.maruyasu-fil.co.jp

TECHNICAL DETAILS

YARN DESCRIPTION :	PREMIUM HIGH STRETCH
COMPOSITION:	VISCOSE72% POLYAMIDE(NYLON)28%
COUNT:	Nm.2/80
TYPE OF DYEING:	Hank / About 250g hank
KNITTING:	18G-1PLY, 16G-1PLY
STOCK SERVICE:	YES Minimum=1.0kg L/T:dyeing=2-3weeks
OWN COLOR:	YES Minimum=3.0kg L/T:dyeing=2-3weeks WOTE: In case no stock of RW / spinning=6-8weeks+dyeing 2-3weeks
FINISHING:	 Washing for 10 min with some softener (Water temp. 35°C) Dewatering for 1min Tumble dry for 3min Press with a lot of steam X It is necessary to make specific trials in your own knits before starting production since the final result always depends on your equipment and the tension and stitch you choose.
SPECIAL CARES:	 The cone should not be rewinded since not appropriate winding could jeapardize the yarn quality. This yarn is dyed in hunks, and has the knots in composition, please knit with care to avoid the knots
CARE INSTRUCTION:	