



MARUYASU Corporation

3-21-5 RYOGOKU SUMIDAKU

TOKYO 130 0026 JAPAN

www.maruyasu-fil.co.jp

TECHNICAL DETAILS

YARN DESCRIPTION :	SPUGNA MOLE
COMPOSITION:	WOOL86% POLYESTER14%
COUNT:	Nm.1/1.9
TYPE OF DYEING:	Hank
KNITTING:	3G-1PLY
STOCK SERVICE:	YES / Stock only ★ mark Minimum=1kg L/T:dyeing 2-3weeks
OWN COLOR:	YES Minimum=4kg L/T:dyeing=2-3weeks ※NOTE: In case no stock of RW / spinning 8-10weeks+dyeing 2-3weeks+chenille 10days
FINISHING:	• Washing 5 min with some softener (Water temp. 35°C) • Dehydrator 1min • Drying 3min • Press with a lot of steam. ※It is necessary to make specific trials in your own knits before starting production since the final result always depends on your equipment and the tension and stitch you choose.
SPECIAL CARES:	1. The cone should not be rewinded since not appropriate winding could jeopardize the yarn quality. 2. This yarn is dyed in hunks, and has the knots in composition, please knit with care to avoid the knots
CARE INSTRUCTION:	