

MARUYASU Corporation

3-21-5 RYOGOKU SUMIDAKU TOKYO 130 0026 JAPAN www.maruvasu-fil.co.ip

TECHNICAL DETAILS

YARN DESCRIPTION: SPUGNA TAM

COMPOSITION: WOOL83% POLYAMIDE(NYLON)17%

COUNT: Nm.1/7

TYPE OF DYEING: Hank

KNITTING: 7G-1PLY, 10G-1PLY

STOCK SERVICE: YES

Minimum=1cone (0.8kg)

L/T:dyeing 2-3weeks

OWN COLOR: YFS

> Minimum=4 cones (3.2kg) L/T:dyeing=2-3weeks

**NOTE: In case no stock of RW / spinning 8-10weeks+dyeing 2-3weeks

FINISHING: · Washing 5 min with some softener (Water temp. 35°C)

· Dehydrator 1min

· Drying 3min

· Press with a lot of steam.

XIt is necessary to make specific trials in your own knits before starting production since the final result always depends on your equipment and

the tension and stitch you choose.

SPECIAL CARES: 1. The cone should not be rewinded since not appropriate winding could

jeapardize the yarn quality.

2. This yarn is dyed in hunks, and has the knots in composition, please knit

with care to avoid the knots

CARE INSTRUCTION:











