

Testing Report



Colour Fastness	Test Items	Methods of Testing	Colour No.	1 SPU200	2	3	4	5	6	
	Colour Fastness	Ultraviolet carbon arc lamp light (Grade)	JIS L 0842	change in colour	/					
Washing and Laundering (Grade)		JIS L 0844	change in colour							
		Method A-2	staining							
Perspiration (Grade)		JIS L 0848	acid	change in colour						
			alkali	staining						
Rubbing (Grade)		JIS L 0849 Type II	dry							
Water (Grade)		JIS L 0846	wet							
Dry cleaning (Grade)		JIS L 0860 Method A-1	change in colour							
	staining									
Bleeding (Grade)	DAIMARU Method I	solution staining								
Pilling (Grade)	JIS L 1076 Method A	3hours	(2.5)							
		5hours	(2.0)							

() Standard Unattained

SAMP	1	2	3	4	5	6
	IVORY					



Applicant	MONTELUCE/MARUYASU Corporation	
	OKUBO	
	3-21-5,Ryogoku, Sumida-Ku, Tokyo, Japan	
TEL: +81-3-3633-5561		
FAX: +81-3-3633-5531		
Article	SPUGNA 1/4 (5G-1P)	
	YA0442	
	1 Piece	
WOOL		100%

Laboratory	THE JAPAN COTTON & STAPLE FIBER FABRIC INSPECTING INSTITUTE FOUNDATION	
	1-10-5, Komagome, Toshima-ku, Tokyo, Japan	
	TEL 03-3943-3174	
	FAX 03-3943-3183	
	Date	2021/11/1
	Test No.	TO-2108810
	InspectionHouse	Tokyo Test Center
Inspector	<i>S. Sato</i>	
Adjacent Fabric	Cotton / Nylon (multifiber fabric)	

Quantitative analysis of fibre mixtures (%)	/
JIS L 1030-2	