

**MARUYASU Corporation**

3-21-5 RYOGOKU SUMIDAKU

TOKYO 130 0026 JAPAN

[www.maruyasu-fil.co.jp](http://www.maruyasu-fil.co.jp)**TECHNICAL DETAILS**

YARN DESCRIPTION :	OLIVETTE
COMPOSITION:	RECYCLED WOOL60% RECYCLED POLYAMIDE(NYLON)20% RECYCLED VISCOSE20%
COUNT:	Nm.1/3.8
TYPE OF DYEING:	TOP DYEING
KNITTING:	5G-1PLY
STOCK SERVICE:	YES Minimum=1kg L/T:Top dyeing+Spinning 8-10weeks *The production leadtime is changed depending on the situation
OWN COLOR:	NO
FINISHING:	<ul style="list-style-type: none"><li>• Washing 5 min with some softener (Water temp. 35°C)</li><li>• Dehydrator 1min</li><li>• Drying 3min</li><li>• Press with a lot of steam.</li></ul> ※It is necessary to make specific trials in your own knits before starting production since the final result always depends on your equipment and the tension and stitch you choose.
SPECIAL CARES:	1. The cone should not be rewinded since not appropriate winding could jeopardize the yarn quality.
CARE INSTRUCTION:	     