

MARUYASU Corporation

3-21-5 RYOGOKU SUMIDAKU TOKYO 130 0026 JAPAN www.maruyasu-fil.co.jp

TECHNICAL DETAILS

YARN DESCRIPTION:	RIVIERA FINE
COMPOSITION:	COTTON 100%
COUNT:	Nm.1/22.8
TYPE OF DYEING:	Cone
KNITTING:	12G-1P
STOCK SERVICE:	YES
	Minimum=1.0kg
	L/T:dyeing=3-4weeks
OWN COLOR:	YES
	Minimum=3.0kg
	L/T:dyeing=3-4weeks
	**NOTE: In case no stock of RW / spinning=8-10weeks+dyeing 3-4weeks
FINISHING:	· Washing for 10 min with some softener (Water temp. 35°C)
	· Dewatering for 1min
	Tumble dry for 3min
	Press with a lot of steam
	* It is necessary to make specific trials in your own knits before starting
	production since the final result always depends on your equipment and
	the tension and stitch you choose.
CDECIAL CADEC.	1. The core should not be requireded since not engreenists winding equid
SPECIAL CARES:	The cone should not be rewinded since not appropriate winding could
	jeapardize the yarn quality.
	This item is dyed in cones and it may have the color differences between inside and outside of cones. We recommend to knit with
	more thread guides. We pay attention to this color difference, and
	we are not able to guarantee this problem if you have.
	3. Striped or jacquard knitwear, dry cleaning is recommend.
ΓECHNICAL	We recommend knitting with double face stitches like half cardigan or full
RECOMMENDATION	needles stiches.
	This item is mercerized with a special solvent. It has a cross-sectional
	structure that reflects light and gives it a luster.
	In the stretching process, some non-uniformity occurs and it causes the

CARE INSTRUCTION:













