

## **MARUYASU** Corporation

3-21-5 RYOGOKU SUMIDAKU TOKYO 130 0026 JAPAN www.maruyasu-fil.co.jp

## **TECHNICAL DETAILS**

YARN DESCRIPTION :	ELIZABETH	
COMPOSITION:	KID MOHAIR58% WOOL21% SILK21%	
COUNT:	Nm.1/12	
TYPE OF DYEING:	Hank/ About 250g per hank	
KNITTING:	7G-1PLY	
STOCK SERVICE:	YES Minimum=1kg L/T:dyeing 3-4weeks	
OWN COLOR:	YES Minimum=3kg L/T:dyeing=3-4weeks	
FINISHING:	<ul> <li>*NOTE: In case no stock of RW / spinning 8-10weeks+dyeing 3-4weeks</li> <li>• Washing 5 min with some softener (Water temp. 35°C)</li> <li>• Dehydrator 1min</li> </ul>	S
	Drying 3min     Press with a lot of steam.	
	% It is necessary to make specific trials in your own knits before starting	
	production since the final result always depends on your equipment ar	
	the tension and stitch you choose.	
SPECIAL CARES:	1. The cone should not be rewinded since not appropriate winding could jeapardize the yarn quality.	
	2. This yarn is dyed in hunks, and has the knots in composition, please k	nit
	with care to avoid the knots	
CARE INSTRUCTION:		