

Testing Report

Test Items		Methods of Testing		Colour No.	1 Graige	2	3	4	5	6
Colour Fastness	Ultraviolet carbon arc lamp light (Grade)	JIS L 0842		change in colour						
	Washing and Laundering (Grade)	JIS L 0844		change in colour						
		Method A-2		staining						
	Perspiration (Grade)	JIS L 0848	acid	change in colour						
			alkali	staining						
	Rubbing (Grade)	JIS L 0849 Type II		dry						
				wet						
	Water (Grade)	JIS L 0846		change in colour						
				staining						
Dry cleaning (Grade)	JIS L 0860		change in colour							
	Method A-1		staining							
				solution staining						
Light and Perspiration (Grade)	JIS L 0888	acid	change in colour							
	Method B		alkali	change in colour						
Water Drop (Grade)	JIS L 0853		change in colour							
Determination of formaldehyde JIS L 1041 Method B (ppm)										
Dimensional Change	Steep Method (%)	JIS L 1096		warp						
		Method C		weft						
	Pressing Method (%)	JIS L 1096		warp						
		Method H-2		weft						
	Dry cleaning Method (%)	JIS L 1096		warp						
		Method J-1 Tumbler drying		weft						
Washer Method (%)	JIS L 1096		warp							
	Method F-2 Tumbler drying		weft							
Electric washing machine Method (%)	JIS L 1930		warp							
	C4M Line drying		weft							
Strength	Snag (Grade)	JIS L 1058 Method D-1		1hour	3.5					
	Water absorbency of textiles (second)	1907		initial	1					
		Dripping method		after*	1					
	Water vapour permeability of textiles (g/m ² ·h)	JIS L 1099 Method A-1			377					
	Tearing Strength (N)	JIS L 1096		warp						
Method D		weft								
Determination of pH of aqueousextract		ISO 3071								

*Pretreatment with JIS L 1930 Method C4M 5 times Line drying.

Applicant	MONTELUCE/MARUYASU Corporation
	Okubo
Article	AIRISOL
	PQ0031
	1 Piece

Laboratory	THE JAPAN COTTON & STAPLE FIBER FABRIC INSPECTING INSTITUTE FOUNDATION	
	1-10-5, Komagome, Toshima-ku, Tokyo, Japan	
	TEL 03-3943-3174 FAX 03-3943-3183	
	Date	2025/3/5
	Test No.	TO-2502715-2-1/2
	InspectionHouse	Tokyo Test Center
	Inspector	S. Sato
Adjacent Fabric		Cotton / Nylon (multifiber fabric)

Quantitative analysis of fibre mixtures (%)	
JIS L 1030-2	

試(東)様式 TO-5-2

SAMPLE	1 Graige	2	3	4	5	6
	MENKEN	MENKEN				