This report is effective for applied samples only, and not for the lot.

Testing Report

	Test Items	Methods of Testing		Colour No.	1 AG27	2	3	4	5	6
Colour Fastness	Ultraviolet carbon arc lamp light (Grade)	JIS L 0842		change in colour						
	Washing and Laundering (Grade)	JIS L 0844 Method A-2		change in colour						
				staining						
				solution staining						
	Perspiration (Grade)	JIS L 0848	acid	change in colour						
				staining						
			alkali	change in colour						
				staining						
	Rubbing (Grade)	JIS L 0849 Type Ⅱ		dry						
				wet						
	Water (Grade)	JIS L 0846		change in colour						
				staining						
	Dry cleaning (Grade)	JIS L 0860 Method A-1		change in colour						
				staining						
				solution staining						
	Light and Perspiration (Grade)	JIS L 0888 Method B	acid	change in colour						
			alkali	change in colour						
	Water Drop (Grade)	JIS L 0853		change in colour						
	Determination of formaldehyde JIS L 1041 Method B (ppm)									
Dimensional Change	Steep Method (%)	JIS L 1096 Method C		warp						
				weft						
	Pressing Method (%)	JIS L 1096 Method H-2		warp						
				weft						
	Dry cleaning Method (%)	JIS L 1096 Method J-1 Tumbler drying		warp						
				weft						
	Electric washing machine Method (%)	JIS L 1930 No.C4M screen drying		warp	-1.8					
				weft	-1.3					
	Electric washing machine Method (%)	JIS L 1930 No.C4H screen drying		warp	-1.5					
				weft	-0.3					
Strength	Pilling (Grade)	JIS L 1076 Method A		3hour						
				5hour						
	Tearing Strength (N)	JIS L 1096 Method D		warp						
				weft						
	Water absorbency of textiles (second)	1907 Dripping method		initial						
				after						
	Water vapour permeability of textiles (g/m²·h)	JIS L 1099 Method A-1								
	Cool touch feeling property (W/cm²)	JIS L 1927								

SAMPLE	1 BABYBLUE	2	3	4	5	6
	MENKEN					

Applicant	MONTELUCE／MARUYASU Corporation Katano
Article	ALLONGE+e SL0051 1 Piece

polyester 73%
flax 27%

Laboratory	
	THE JAPAN COTTON & STAPLE FIBER FABRIC INSPECTING INSTITUTE FOUNDATION 1-10-5, Komagome, Toshima-ku, Tokyo, Japan
	TEL 03-3943-3174 FAX 03-3943-3183
Date	2026/10/1
Test No.	TO-2608117-②
InspectionHouse	Tokyo Test Center
Inspector	M. Mori
Adjacent Fabric	Cotton / Nylon (multifiber fabric)

Quantitative analysis of fibre mixtures (%) JIS L 1030-2	
	polyester 71.7 flax 28.3

試(東)様式 TO－5－4－2