

Testing Report

Test Items		Methods of Testing	Colour No.	1 VAL26	2 VAL61	3 VAL62	4 VAL1	5 VAL63	6 VAL64
Colour Fastness	Ultraviolet carbon arc lamp light (Grade)	JIS L 0842	change in colour	>4	>4	>4	>4	>4	>4
	Washing and Laundering (Grade)	JIS L 0844 Method A-2	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	5 5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
			solution staining	5	4-5	4-5	4-5	4-5	4-5
	Perspiration (Grade)	JIS L 0848	acid	change in colour	4-5	4-5	4-5	4-5	4-5
				staining	5 5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
			alkali	change in colour	4-5	4-5	4-5	4-5	4-5
				staining	5 5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
	Rubbing (Grade)	JIS L 0849 Type II	dry	4-5	4-5	4-5	4-5	4-5	4-5
			wet	4-5	4-5	4-5	4-5	4-5	4-5
Colour Fastness	Water (Grade)	JIS L 0846	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	5 5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
	Dry cleaning (Grade)	JIS L 0860 Method A-1	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	5	4-5	4-5	4-5	4-5	4-5
			solution staining	5	4-5	4-5	4-5	4-5	4-5
	Bleeding (Grade)	DAIMARU Method I	staining	5	5	4-5	4-5	4-5	4-5

Test Items		Methods of Testing	Colour No.	7 VAL65	8 VAL27	9 VAL9	10 VAL53	11 VAL10	12 VAL103
Colour Fastness	Ultraviolet carbon arc lamp light (Grade)	JIS L 0842	change in colour	4	>4	>4	>4	>4	>4
	Washing and Laundering (Grade)	JIS L 0844 Method A-2	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
			solution staining	4-5	4-5	4-5	4-5	4-5	4-5
	Perspiration (Grade)	JIS L 0848	acid	change in colour	4-5	4-5	4-5	4-5	4-5
				staining	4-5 4	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
			alkali	change in colour	4-5	4-5	4-5	4-5	4-5
				staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
	Rubbing (Grade)	JIS L 0849 Type II	dry	4-5	4-5	4-5	4-5	4-5	4-5
			wet	4	4-5	4-5	4	3-4	4-5
Colour Fastness	Water (Grade)	JIS L 0846	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	4-5 4	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
	Dry cleaning (Grade)	JIS L 0860 Method A-1	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	4-5	4-5	4-5	4-5	4-5	4-5
			solution staining	4-5	4-5	4-5	4-5	4-5	4-5
	Bleeding (Grade)	DAIMARU Method I	staining	4-5	4-5	4-5	4-5	4-5	4-5

1 white	2 off white	3 ecru beige	4 L beige mix	5 L beige	6 L brown
7 brown	8 sky mix	9 blue mix	10 royal blue	11 navy mix	12 D blue mix

Applicant	MONTELUCE/MARUYASU Corporation	
	OKUBO	
Article	1/59 VALLONE +e	
	SL0058	
	28 Pieces	
POLYESTER75% COTTON25%		

Laboratory	THE JAPAN COTTON & STAPLE FIBER FABRIC INSPECTING INSTITUTE FOUNDATION	
	1-10-5, Komagome, Toshima-ku, Tokyo, Japan	
	TEL 03-3943-3174 FAX 03-3943-3183	
	Date	2025/9/5
	Test No.	TO-2506722-2-1/3
	InspectionHouse	Tokyo Test Center
Inspector	S. Sato	
	Adjacent Fabric	Cotton / Nylon (multifiber fabric)

Quantitative analysis of fibre mixtures (%)	
JIS L 1030-2	試(東)様式 TO-5-2

Testing Report

Test Items		Methods of Testing	Colour No.	13 VAL66	14 VAL40	15 VAL34	16 VAL38	17 VAL52	18 VAL57
Colour Fastness	Ultraviolet carbon arc lamp light (Grade)	JIS L 0842	change in colour	>4	>4	>4	4	>4	>4
	Washing and Laundering (Grade)	JIS L 0844 Method A-2	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
			solution staining	4-5	4-5	4-5	4-5	4-5	4-5
	Perspiration (Grade)	JIS L 0848	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			acid staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
			alkali change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
	Rubbing (Grade)	JIS L 0849 Type II	dry	4-5	4-5	4-5	4-5	4-5	4-5
			wet	3	3	4	4-5	4	4-5
Colour Fastness	Water (Grade)	JIS L 0846	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
	Dry cleaning (Grade)	JIS L 0860 Method A-1	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	4-5	4-5	4-5	4-5	4-5	4-5
			solution staining	4-5	4-5	4-5	4-5	4-5	4-5
	Bleeding (Grade)	DAIMARU Method I	staining	4-5	4-5	4-5	4-5	4-5	4-5
Test Items		Methods of Testing	Colour No.	19 VAL51	20 VAL31	21 VAL11	22 VAL68	23 VAL8	24 VAL32
Colour Fastness	Ultraviolet carbon arc lamp light (Grade)	JIS L 0842	change in colour	>4	>4	>4	>4	4	>4
	Washing and Laundering (Grade)	JIS L 0844 Method A-2	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
			solution staining	4-5	4-5	4-5	4-5	4-5	4-5
	Perspiration (Grade)	JIS L 0848	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			acid staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
			alkali change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
	Rubbing (Grade)	JIS L 0849 Type II	dry	4-5	4-5	4-5	4-5	4-5	4-5
			wet	4-5	4-5	4	4-5	4-5	4
Colour Fastness	Water (Grade)	JIS L 0846	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
	Dry cleaning (Grade)	JIS L 0860 Method A-1	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
			staining	4-5	4-5	4-5	4-5	4-5	4-5
			solution staining	4-5	4-5	4-5	4-5	4-5	4-5
	Bleeding (Grade)	DAIMARU Method I	staining	4-5	4-5	4-5	4-5	4-5	4-5

Applicant	MONTELUCE/MARUYASU Corporation	
	OKUBO	
Article	1/59 VALLONE +e	
	SL0058	
	28 Pieces	
POLYESTER 75%		
COTTON 25%		

Laboratory	THE JAPAN COTTON & STAPLE FIBER FABRIC INSPECTING INSTITUTE FOUNDATION	
	1-10-5, Komagome, Toshima-ku, Tokyo, Japan	
	TEL 03-3943-3174 FAX 03-3943-3183	
	Date	2025/9/5
	Test No.	TO-2506722-2-2/3
	InspectionHouse	Tokyo Test Center
	Inspector	S. Seto
Adjacent Fabric		Cotton / Nylon (multifiber fabric)

13 D green	14 dark navy	15 cian mix	16 lime mix	17 green	18 orange
19 yellow	20 lemon mix	21 raphia mix	22 L purple	23 mauve mix	24 magenta mix

Quantitative analysis of fibre mixtures (%)	
JIS L 1030-2	TO-5-2

Testing Report

Test Items		Methods of Testing	Colour No.	25 VAL41	26 VAL17	27 VAL19	28 VAL23B	29	30
Colour Fastness	Ultraviolet carbon arc lamp light (Grade)	JIS L 0842	change in colour	>4	>4	>4	>4		
	Washing and Laundering (Grade)	JIS L 0844 Method A-2	change in colour	4-5	4-5	4-5	4-5		
			staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5		
			solution staining	4-5	4-5	4-5	4-5		
	Perspiration (Grade)	JIS L 0848	acid	change in colour	4-5	4-5	4-5	4-5	
				staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	
			alkali	change in colour	4-5	4-5	4-5	4-5	
				staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	
	Rubbing (Grade)	JIS L 0849 Type II	dry	4-5	4-5	4-5	4-5		
			wet	4	4-5	3	3		
Colour Fastness	Water (Grade)	JIS L 0846	change in colour	4-5	4-5	4-5	4-5		
			staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5		
	Dry cleaning (Grade)	JIS L 0860 Method A-1	change in colour	4-5	4-5	4-5	4-5		
			staining	4-5	4-5	4-5	4-5		
			solution staining	4-5	4-5	4-5	4-5		
	Bleeding (Grade)	DAIMARU Method I	staining	4-5	4-5	4-5	4-5		
Test Items		Methods of Testing	Colour No.	31	32	33	34	35	36
Colour Fastness	Ultraviolet carbon arc lamp light (Grade)	JIS L 0842	change in colour						
	Washing and Laundering (Grade)	JIS L 0844 Method A-2	change in colour						
			staining						
			solution staining						
	Perspiration (Grade)	JIS L 0848	acid	change in colour					
				staining					
			alkali	change in colour					
				staining					
	Rubbing (Grade)	JIS L 0849 Type II	dry						
			wet						
Colour Fastness	Water (Grade)	JIS L 0846	change in colour						
			staining						
	Dry cleaning (Grade)	JIS L 0860 Method A-1	change in colour						
			staining						
			solution staining						
	Bleeding (Grade)	DAIMARU Method I	staining						
SAMPLE	25 rose	26 M gray mix	27 D gray mix	28 black	29	30			
	31	32	33	34	35	36			

Applicant	MONTELUCE/MARUYASU Corporation	
	OKUBO	
Article	1/59 VALLONE +e	
	SL0058	
	28 Pieces	
POLYESTER 75% COTTON 25%		
Laboratory	THE JAPAN COTTON & STAPLE FIBER FABRIC INSPECTING INSTITUTE FOUNDATION	
	1-10-5, Komagome, Toshima-ku, Tokyo, Japan	
	TEL 03-3943-3174 FAX 03-3943-3183	
	Date	2025/9/5
	Test No.	TO-2506722-2-3/3
	InspectionHouse	Tokyo Test Center
	Inspector	S. Sato
Adjacent Fabric	Cotton / Nylon (multifiber fabric)	

Quantitative analysis of fibre mixtures (%)	
JIS L 1030-2	

試(東)様式 TO-5-2