

生地品質検査報告書

試験項目		試験方法		生地	1 IVL000	2 IVL110	3 IVL1	4 IVL2	5 IVL4	6 IVL3	7 IVL5	8 IVL6	
染色堅牢度	耐光(級)	JIS L 0842		変退色	4	4	4	4	4	4	4	4	
	洗濯(級)	JIS L 0844 A-2号		変退色	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	
				汚染	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
				液汚染	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	
	汗(級)	JIS L 0848	酸	変退色	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	
			アルカリ	汚染	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
				変退色	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
	摩擦(級)	JIS L 0849 Ⅱ形		乾燥	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	
				湿潤	4-5	4-5	4-5	4-5	3-4	2-3	4-5	4-5	
	水(級)	JIS L 0846		変退色	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	
			汚染	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5		

備考

()は基準未達

依頼者指定項目

1 アイボリー	2 オフホワイト	3 プラチナ	4 オリーブ	5 ブラック	6 ダークブラウン	7 グレー	8 イグ
9 ダークグレー	10 トープ	11 スカイブルー	12 スカーレット	13 チャコール	14 ブラック	15	16

納入先	会社名	
	ブランド名	
納入者	会社名	丸安毛糸(株)
	担当者	大久保
	品名	1/2.3 IVORY LIGHT アイボリーライト
	品番	YA0520
	色数	14点
依頼書記載 混用率(%)	綿	95
	ナイロン	4
	ポリウレタン	1
試験 機関名	一般財団法人 メンケン品質検査協会 東京試験センター 〒170-0003 東京都豊島区駒込1-10-5 TEL 03-3943-3174 FAX 03-3943-3183	
受付	2026年7月31日	
発行	2026年8月31日 報告書No. TO-2606568-1	
処理	受付	担当
	岩崎	山本
添付白布	綿・ナイロン・多織交織布	