This report is effective for applied samples only, and not for the lot.

Testing Report

Test Items			Methods of Testing	Colour No.	1 IVL000	2 IVL110	3 IVL1	4 IVL2	5 IVL4	6 IVL3
Colour Fastness	Ultraviolet carbon arc lamp light (Grade)		JIS L 0842	change in colour	4	4	4	4	4	4
	Washing and Laundering (Grade)		JIS L 0844 Method A-2	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
				staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
				solution staining	4-5	4-5	4-5	4-5	4-5	4-5
	Perspiration (Grade)	acid	JIS L 0848	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
				staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
		alkali		change in colour	4-5	4-5	4-5	4-5	4-5	4-5
				staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
	Rubbing (Grade)		JIS L 0849 Type Ⅱ	dry	4-5	4-5	4-5	4-5	4-5	4-5
				wet	4-5	4-5	4-5	4-5	3-4	2-3
	Water (Grade)		JIS L 0846	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
				staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
	Dry cleaning (Grade)		JIS L 0860 Method A-1	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
				staining	4-5	4-5	4-5	4-5	4-5	4-5
				solution staining	4-5	4-5	4-5	4-5	4-5	4-5
	Bleeding (Grade)		DAIMARU Method I	staining	4-5	4-5	4-5	4-5	4-5	4-5

Test Items			Methods of Testing	Colour No.	7 IVL5	8 IVL6	9 IVL10	10 IVL7	11 IVL8	12 IVL9
Colour Fastness	Ultraviolet carbon arc lamp light (Grade)		JIS L 0842	change in colour	4	4	4	4	4	>4
	Washing and Laundering (Grade)		JIS L 0844 Method A-2	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
				staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
				solution staining	4-5	4-5	4-5	4-5	4-5	4-5
	Perspiration (Grade)	acid	JIS L 0848	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
				staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
		alkali		change in colour	4-5	4-5	4-5	4-5	4-5	4-5
				staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
	Rubbing (Grade)		JIS L 0849 Type Ⅱ	dry	4-5	4-5	4-5	4-5	4-5	4-5
				wet	4-5	4-5	3-4	4-5	(2)	(2)
	Water (Grade)		JIS L 0846	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
				staining	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5	4-5 4-5
	Dry cleaning (Grade)		JIS L 0860 Method A-1	change in colour	4-5	4-5	4-5	4-5	4-5	4-5
				staining	4-5	4-5	4-5	4-5	4-5	4-5
				solution staining	4-5	4-5	4-5	4-5	4-5	4-5
	Bleeding (Grade)		DAIMARU Method I	staining	4-5	4-5	4-5	4-5	4-5	(4)

( ) Standard Unattained

SAMPLE

1 ivory	2 offwhite	3 platinum	4 olive	5 black	6 D.brown
7 gray	8 egg	9 D.gray	10 taupe	11 skyblue	12 scarlet



Applicant	MONTELUCE／MARUYASU Corporetion OKUBO
Article	1/2.3 IVORY LIGHT YA0520 14 Pieces

COTTON	95%
NYLON	4%
POLYURETHANE	1%

Laboratory

THE JAPAN COTTON & STAPLE FIBER FABRIC INSPECTING INSTITUTE FOUNDATION
1-10-5, Komagome,
Toshima-ku, Tokyo,
Japan
TEL 03-3943-3174
FAX 03-3943-3183

Date	2026/8/31
Test No.	TO-2606568-2-1/2
InspectionHouse	Tokyo Test Center
Inspector	S. Sato
Adjacent Fabric	Cotton / Nylon (multifiber fabric)

Quantitative analysis of fibre mixtures (%)
JIS L 1030-2

試(東)様式 TO－5－2

This report is effective for applied samples only, and not for the lot.

Testing Report

Test Items			Methods of Testing	Colour No.	13 IVL770	14 IVL999	15	16	17	18
Colour Fastness	Ultraviolet carbon arc lamp light (Grade)		JIS L 0842	change in colour	4	>4				
	Washing and Laundering (Grade)		JIS L 0844 Method A-2	change in colour	4-5	4-5				
				staining	4-5 4-5	4-5 4-5				
				solution staining	4-5	4-5				
	Perspiration (Grade)	acid	JIS L 0848	change in colour	4-5	4-5				
				staining	4-5 4-5	4-5 4-5				
		alkali		change in colour	4-5	4-5				
				staining	4-5 4-5	4-5 4-5				
	Rubbing (Grade)		JIS L 0849 Type II	dry	4-5	4-5				
				wet	2-3	(1-2)				
	Water (Grade)		JIS L 0846	change in colour	4-5	4-5				
				staining	4-5 4-5	4-5 4-5				
	Dry cleaning (Grade)		JIS L 0860 Method A-1	change in colour	4-5	4-5				
				staining	4-5	4-5				
				solution staining	4-5	4-5				
	Bleeding (Grade)		DAIMARU Method I	staining	4-5	4-5				

Test Items			Methods of Testing	Colour No.	19	20	21	22	23	24
Colour Fastness	Ultraviolet carbon arc lamp light (Grade)		JIS L 0842	change in colour						
	Washing and Laundering (Grade)		JIS L 0844 Method A-2	change in colour						
				staining						
				solution staining						
	Perspiration (Grade)	acid	JIS L 0848	change in colour						
				staining						
		alkali		change in colour						
				staining						
	Rubbing (Grade)		JIS L 0849 Type II	dry						
				wet						
	Water (Grade)		JIS L 0846	change in colour						
				staining						
	Dry cleaning (Grade)		JIS L 0860 Method A-1	change in colour						
				staining						
				solution staining						
	Bleeding (Grade)		DAIMARU Method I	staining						

( ) Standard Unattained

SAMPLE						
	13 charcoal	14 black	15	16	17	18
	19	20	21	22	23	24

Applicant	MONTELUCE／MARUYASU Corporation OKUBO
Article	1/2.3 IVORY LIGHT YA0520 14 Pieces

COTTON	95%
NYLON	4%
POLYURETHANE	1%

Laboratory	
	THE JAPAN COTTON & STAPLE FIBER FABRIC INSPECTING INSTITUTE FOUNDATION 1-10-5, Komagome, Toshima-ku, Tokyo, Japan
	TEL 03-3943-3174 FAX 03-3943-3183
Date	2026/8/31
Test No.	TO-2606568-2-2/2
InspectionHouse	Tokyo Test Center
Inspector	S. Sato
Adjacent Fabric	Cotton / Nylon (multifiber fabric)

Quantitative analysis of fibre mixtures (%) JIS L 1030-2	

試(東)様式 TO－5－2