

Testing Report

Test Items		Methods of Testing	Colour No.	1	2	3	4	5	6
Colour Fastness	Ultraviolet carbon arc lamp light (Grade)	JIS L 0842	change in colour						
	Washing and Laundering (Grade)	JIS L 0844 Method A-2	change in colour						
			staining						
			solution staining						
	Perspiration (Grade)	JIS L 0848	acid change in colour						
			staining						
		alkali	change in colour						
			staining						
	Rubbing (Grade)	JIS L 0849 Type II	dry wet						
	Water (Grade)	JIS L 0846	change in colour						
Dimensional Change	Dry cleaning (Grade)	JIS L 0860 Method A-1	change in colour						
			staining						
			solution staining						
	Light and Perspiration (Grade)	JIS L 0888 Method B	acid change in colour						
			alkali change in colour						
	Water Drop (Grade)	JIS L 0853	change in colour						
	Determination of formaldehyde JIS L 1041 Method B(ppm)								
	Steep Method (%)	JIS L 1096 Method C	warp						
			weft						
	Pressing Method (%)	JIS L 1096 Method H-2	warp						
			weft						
Strength	Dry cleaning Method (%)	JIS L 1096 Method J-1 Tumbler drying	warp						
			weft						
	Electric washing machine Method (%)	JIS L 1930 No.C4G screen drying neutral detergent	warp						
			weft						
	Electric washing machine Method (%)	JIS L 1930 No.C4H flat drying	warp	-13.8					
			weft	-11.3					
	Pilling (Grade)	JIS L 1076 Method A	3hour	3.5					
			5hour	2.5					
	Tearing Strength (N)	JIS L 1096 Method D	warp						
			weft						
	Water absorbency of textiles (second)	1907 Dripping method	initial						
	Water vapour permeability of textiles (g/m ² ·h)	JIS L 1099 Method A-1	after						
	Cool touch feeling property (W/cm ²)	JIS L 1927							
SAMPLE	1 BLACK	2	3	4	5	6			
									

Applicant	MONTELUCE/MARUYASU Corporation	
	Okubo	
Article	1/2.3 NEO PAPER2.3	
	BS0046	
	1 Piece	
CUPRO 100%		
Laboratory	THE JAPAN COTTON & STAPLE FIBER FABRIC INSPECTING INSTITUTE FOUNDATION	
	1-10-5, Komagome, Toshima-ku, Tokyo, Japan	
	TEL 03-3943-3174 FAX 03-3943-3183	
	Date	2026/7/8
	Test No.	TO-2605559-(2)
	InspectionHouse	Tokyo Test Center
	Inspector	M. Mori
Adjacent Fabric	Cotton / Nylon (multifiber fabric)	
Quantitative analysis of fibre mixtures (%)		
JIS L 1030-2		
試(東)様式 TO-5-4-2		