

**MARUYASU Corporation**

3-21-5 RYOGOKU SUMIDAKU

TOKYO 130 0026 JAPAN

www.maruyasu-fil.co.jp

Date: 29/06/2026

TECHNICAL DETAILS

YARN DESCRIPTION :	PLASIR		
COMPOSITION:	WOOL 46% COTTON 44% BABY ALPACA 7% POLYAMID (NY) 3%		
COUNT:	Nm.1/2	1 CONE:	1.0KG
TYPE OF DYEING:	Hank/ About 250g per hank		
KNITTING:	5G-1P		
STOCK SERVICE:	YES Minimum=1kg L/T:dyeing 3-4weeks		
OWN COLOR:	YES Minimum=3kg L/T:dyeing=3-4weeks ※NOTE: In case no stock of RW / spinning 8-10weeks+dyeing 3-4weeks		
FINISHING:	• Washing 5 min with some softener (Water temp. 35°C) • Dehydrator 1min • Drying 3min • Press with a lot of steam.		
SPECIAL CARES:	1. The cone should not be rewinded since not appropriate winding could jeopardize the yarn quality. 2. This yarn is dyed in hunks, and has the knots in composition, please knit with care to avoid the knots. 3. It is necessary to conduct specific trials and perform quality tests on your own knits before starting production since the final result always depends on your equipment and the tension and stitch you choose.		
CARE INSTRUCTION:	     		